

## 測試報告

報告編號： UG/2013/10078-01 日期： 2013年10月21日 頁數： 1 of 2



台灣阿克蘇諾貝爾塗料股份有限公司

桃園縣中壢市東園路52號

以下測試之樣品係由申請廠商所提供及確認：

產品名稱： 得利竹炭健康居抗甲醛乳膠漆(Dulux FreshAir AF Emulsion)  
 申請廠商： 台灣阿克蘇諾貝爾塗料股份有限公司  
 產品型號： A991K  
 生產或供應廠商： 得利塗料  
 原產國： 台灣  
 送樣日期： 2013年01月10日  
 測試日期： 2013年01月11日  
 去除率物質： 甲醛  
 測試方法： 樣品至入 1m<sup>3</sup> 測試箱，並放入待測標準品氣體，依照客戶指定時間點進行採樣。  
 MDL: 0.1 ppm

### 對照組

NO.	採樣時間點	分析濃度 (ppm)	自然衰減率 (%)
1	0 小時	10.0	---
2	24 小時	8.2	18.0%

### 實驗組

NO.	採樣時間點	分析濃度 (ppm)	去除率 (%)
1	0 小時	10.0	0.00
2	24 小時	<MDL	>99%

備註：1. 本報告不得分離，分離使用無效。

- END -

Signed for and on behalf of  
SGS Taiwan Ltd.

Shin-Jyh Chen  
Shin-Jyh Chen  
Manager



## 測試報告

報告編號：

UG/2013/10078-01

日期：2013年10月21日

頁數：2 of 2



台灣阿克蘇諾貝爾塗料股份有限公司

桃園縣中壢市東園路52號

## 樣品照片



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.